



# TEKASIL

## Sanitar Acetat



TEKASIL sanitar acetat is a permanently elastic, silicone one-component sealant on acetic basis used for sealing glass, ceramics and aluminum in damp places.

### PROPERTIES

- A special additive is preventing the occurrence of moulds on the silicone
- Does not slip in vertical joints
- Excellent adhesion to glass, ceramics, glazed surfaces, aluminum, copelite glass
- Good characteristics
- Movement accommodation up to 25 %
- Resistant to various weather conditions; rain, snow, extreme temperatures
- Resistant to chemicals
- UV resistant
- Low shrinkage at hardening
- Releases acetic acid during hardening
- Long storage life
- A wide selection of colours (see colour chart)

### USE

- For sealing joints in toilets and other damp places
- For sealing joints between ceramics, glass and aluminum
- Not suitable for sealing zinc tin

### TECHNICAL DATA

#### Uncured sealant

Basis		acetic acid silicons
Form		paste
Curing mechanism		moisture curing
Specific gravity		1000 ± 20 kg/m <sup>3</sup>
Skin formation time	23°C/50% rel. humid	10 - 20 min
Hardening time	23°C/50% rel. humid	1 - 2 mm/day
Resistance to flow	ISO 7390	0 mm
Application temperature		+5°C to +40°C

#### Hardened sealant

Hardness Shore A	ISO 868	15 - 25
Tensile Strength	ISO 8339	0,50 - 0,60 MPa
Module E 100%	ISO 8339	0,30 MPa
Elongation at break	ISO 8339	300 - 400%
Tensile strength	ISO 37 rod 1	> 1,10 MPa
Elongation at break	ISO 37 rod 1	> 500%
Change in volume	ISO 10563	< 10%
Elastic recovery	ISO 7389	98%
Temperature resistance		-40°C to +180°C

## APPLICATION

### Surface preparation:

The surface of the joint must be hard, clean, dust and fat free. Remove all separated and badly attached pieces.

### Joint and cartridge preparation:

- If you want joints to look nice tape the edges with masking tape.
- Cut the cartridge at the top and screw on the nozzle, which has to be cut according to the width of the joint and placed in the gun. During work interruption release the handle on the gun and pull the piston back.
- The sealant should be applied as evenly as possible.
- At the end, level the sealant with an appropriate instrument or a well soaped finger.
- Remove the masking tape before the sealant starts to harden.
- Fresh sealant and tools can be cleaned with the Tekafin cleaner, hardened sealant should be removed mechanically first and then with a cleaner for hardened silicone Tekapursil S or Apursil.

Joint depth (mm)	Joint width (mm)			
	6	8	10	12
6	8,3	6,2	5	4,2
8		4,7	3,7	3,1
10			3,0	2,5
12				2,1

The table shows how many linear metres of joints we can seal with one 300 ml cartridge relative to the width and depth of the joint.

## PACKING

- 300 ml cartridges (A carton of 20 pieces)
  - 60 ml tube in blister
  - 200 l barrels
  - 300 ml, 400 ml, 600 ml sausages
- Other ways of packing are available on demand.

## STORAGE

24 months in a dry, cool place under 25°C, in the originally sealed package.

## SAFETY PRECAUTIONS

Keep out of the reach of children. Wear suitable gloves. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Use only in well-ventilated areas.

## ATTENTION

The information supplied is accurate to the best of our knowledge and is based on reliable tests and practical experiences. Properties quoted are intended, as a guide and do not therefore constitute a specification. You should thoroughly test any application to be sure that product corresponds to the required performances.